

**AMENDMENTS TO THE CLAIMS**

**Listing of claims:**

This listing of claims replaces all prior versions and listings of claims in the application.

1. (Cancelled)
2. (Previously Presented): A two-component curable composition comprising agent A comprising
  - (A) x parts by weight of a reactive silicon group-containing polyoxypropylene polymer,
  - (B) from 0.1 to 20 parts by weight of a silane coupling agent,
  - (D) from 0.1 to 60 parts by weight of a curing agent for an epoxy resin containing a tertiary amine, and
  - (E) from 0.1 to 30 parts by weight of a primary or secondary amine having a melting point of 20°C or more (provided  $0 < x \leq 100$ ), and agent B comprising
    - (A) 100-x parts by weight of the reactive silicon group-containing polyoxypropylene polymer,
    - (C) from 0.1 to 80 parts by weight of an epoxy resin, and
    - (F) from 0.1 to 5 parts by weight of water.

3. (Previously Presented): The curable composition as claimed in claim 2, wherein the viscosity of the composition is at least 50 Pa·s and at most 200 Pa·s at 23°C, and the structural viscosity index thereof is at least 4.0 and at most 10.

4. (Previously Presented): The curable composition as claimed in claim 2, which further comprises

(G) from 50 to 300 parts by weight of an inorganic filler.

5. (Previously Presented): The curable composition as claimed in claim 2, wherein component (E) is a primary amine.

6. (Previously Presented): A coating material comprising the curable composition as claimed in claim 2.

7. (Previously Presented): The curable composition as claimed in claim 2, wherein component (D) is an araliphatic amine.

8. (Previously Presented): The curable composition as claimed in claim 2, wherein component (D) is a 2, 4, 6-tris(dimethylaminomethylphenol).

9. (New): The curable composition of claim 2, wherein  $x=100$ .